

Stainless Steel 304 Data Sheet

Do you need custom fasteners created with Stainless Steel 304? Since our inception, Elgin Fastener Group has met every challenge of providing Quality, Timely, Cost-effective solutions for specialty fastener applications. Every product is built to your specifications, using your prints if necessary.

Below are the technical specifications of the Stainless Steel 304 Bar Stock we have available to meet your needs.

AISI Type 304 Stainless Steel

Subcategory: Heat Resisting; Metal; Stainless Steel; T 300 Series Stainless Steel

Close Analogs: UNS S30400; AMS 5501, 5513, 5560, 5565; ASME SA182, SA194 (8), SA213, SA240; ASTM A167, A182, A193, A194

Key Words: aisi304, aisi 304, T304, T 304, SUS304, SS304, 304SS, 304 SS, UNS S30400, AMS 5501, AMS 5513, AMS 5560, AMS 5565, AMS 5566, AMS 5567, AMS 5639, AMS 5697, ASME SA182, ASME SA194 (8), ASME SA213, ASME SA240, ASME SA249, ASME SA312, ASME SA320 (B8), ASME SA358, ASME SA376, ASME SA403, ASME SA409, ASME SA430, ASME SA479, ASME SA688, ASTM A167, ASTM A182, ASTM A193, ASTM A194, ASTM A666, FED QQ-S-763, MILSPEC MIL-S-5059, SAE 30304, DIN 1.4301, X5CrNi189, B.S. 304 S 15, EN 58E, PN 86020 (Poland), OH18N9, ISO 4954 X5CrNi189E, ISO 683/13 11, 18-8

Component	Wt. %
С	Max 0.08
Cr	18 / 20
Fe	66.345 / 74
Mn	Max 2
Ni	8 /10.5
Р	Max 0.045
S	Max 0.03
Si	Max 1

Material Notes:

Austenitic Cr-Ni stainless steel. Better corrosion resistance than Type 302. High ductility, excellent drawing, forming, and spinning properties. Essentially non-magnetic, becomes slightly magnetic when cold worked. Low carbon content means less carbide precipitation in the heat-affected zone during welding and a lower susceptibility to intergranular corrosion.

Applications: beer kegs, bellows, chemical equipment, coal hopper linings, cooking equipment, cooling coils, cryogenic vessels, dairy equipment, evaporators, flatware utensils, feedwater tubing, flexible metal hose, food processing equipment, hospital surgical equipment, hypodermic needles, kitchen sinks, marine equipment and

fasteners, nuclear vessels, oil well filter screens, refrigeration equipment, paper industry, pots and pans, pressure vessels, sanitary fittings, valves, shipping drums, spinning, still tubes, textile dyeing equipment, tubing.

Corrosion Resistance: resists most oxidizing acids and salt spray.

Physical Properties	Metric	English	Comments
Density	8 g/cc	0.289 lb/in ³	
Mechanical Properties			
Hardness, Brinell	123	123	Converted from Rockwell B hardness.
Hardness, Knoop	138	138	Converted from Rockwell B hardness.
Hardness, Rockwell B	70	70	
Hardness, Vickers	129	129	Converted from Rockwell B hardness.
Tensile Strength, Ultimate	505 MPa	73200 psi	
Tensile Strength, Yield	215 MPa	31200 psi	at 0.2% offset
Elongation at Break	70 %	70 %	in 50 mm
Modulus of Elasticity	193 /" 200 GPa	28000 /" 29000 ksi	
Poisson/ TM s Ratio	0.29	0.29	
Charpy Impact	325 J	240 ft-lb	
Shear Modulus	86 GPa	12500 ksi	
Electrical Properties			
Electrical Resistivity	7.2e-005 ohm-cm	7.2e-005 ohm-cm	at 20°C (68°F); 1.16E-04 at 650°C (1200°F)
Magnetic Permeability	1.008	1.008	at RT
Thermal Properties			
CTE, linear 20°C	17.3 μm/m-°C	9.61 µin/in-°F	from from 0-100°C
CTE, linear 250°C	17.8 μm/m-°C	9.89 µin/in-°F	at 0-315°C (32-600°F)
CTE, linear 500°C	18.7 μm/m-°C	10.4 µin/in-°F	at 0-650°C
Heat Capacity	0.5 J/g-°C	0.12 BTU/lb-°F	from 0-100°C (32-212°F)
Thermal Conductivity	16.2 W/m-K	112 BTU-in/hr-ft²-°F	at 0-100°C, 21.5 W/m°C at 500°C
Melting Point	1400 /" 1455 °C	2550 /" 2650 °F	
Solidus	1400 °C	2550 °F	
Liquidus	1455 °C	2650 °F	